

106

PTC 02 DEC 2005

10/559584

Document made available under the Patent Cooperation Treaty (PCT)

International application number: PCT/US04/029849

International filing date: 15 September 2004 (15.09.2004)

Document type: Certified copy of priority document

Document details: Country/Office: US
Number: 60/580,489
Filing date: 16 June 2004 (16.06.2004)


Date of receipt at the International Bureau: 11 March 2005 (11.03.2005)

Remark: Priority document submitted or transmitted to the International Bureau in compliance with Rule 17.1(a) or (b)



World Intellectual Property Organization (WIPO) - Geneva, Switzerland
Organisation Mondiale de la Propriété Intellectuelle (OMPI) - Genève, Suisse

1290100



THE UNITED STATES OF AMERICA

TO ALL TO WHOM THESE PRESENTS SHALL COME:

UNITED STATES DEPARTMENT OF COMMERCE

United States Patent and Trademark Office

February 28, 2005

THIS IS TO CERTIFY THAT ANNEXED HERETO IS A TRUE COPY FROM THE RECORDS OF THE UNITED STATES PATENT AND TRADEMARK OFFICE OF THOSE PAPERS OF THE BELOW IDENTIFIED PATENT APPLICATION THAT MET THE REQUIREMENTS TO BE GRANTED A FILING DATE.

APPLICATION NUMBER: 60/580,489

FILING DATE: *June 16, 2004*

RELATED PCT APPLICATION NUMBER: *PCT/US04/29849*



Certified by

W. J. Duckas

Under Secretary of Commerce
for Intellectual Property
and Director of the United States
Patent and Trademark Office

05909 U.S. PTO
061604

PTO/SB/18 (04-04)
Approved for use through 07/31/2006. OMB 0851-0032
U.S. Patent and Trademark Office; U.S. DEPARTMENT OF COMMERCE
Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

PROVISIONAL APPLICATION FOR PATENT COVER SHEET

This is a request for filing a PROVISIONAL APPLICATION FOR PATENT under 37 CFR 1.53(c).

Express Mail Label No. EV 426313695 US

2215 U.S. PTO
60/580489

061604

INVENTOR(S)					
Given Name (first and middle (if any))		Family Name or Surname		Residence (City and either State or Foreign Country)	
Jonathan Whitney		ROBERTS		484 Salter Hill Rd., Arlington, VT 05250 USA	
Dana James		RACKLIFFE		503 Post Rd., Rutland, VT 05701 USA	
Daniel Richard		BERNATCHY		41 Holiday Farm Rd., Bridgewater Corners, VT 05034 USA	
<input type="checkbox"/> Additional inventors are being named on the _____ separately numbered sheets attached hereto					
TITLE OF THE INVENTION (500 characters max)					
MAXIMIZED MICA CONTENT USING A SPECIALTY THIN HIGH TENSILE BACKING MATERIAL					
Direct all correspondence to: CORRESPONDENCE ADDRESS					
<input checked="" type="checkbox"/> Customer Number		23405			
OR					
<input checked="" type="checkbox"/> Firm or Individual Name		MARY LOUISE GIOENI			
Address		HESLIN ROTHENBERG FARLEY & MESITI P.C.			
Address		5 COLUMBIA CIRCLE			
City		ALBANY	State	NEW YORK	ZIP 12203
Country		UNITED STATES	Telephone	(518) 452-5600	Fax (518) 452-5579
ENCLOSED APPLICATION PARTS (check all that apply)					
<input checked="" type="checkbox"/> Specification Number of Pages 4		<input type="checkbox"/> CD(s), Number _____			
<input type="checkbox"/> Drawing(s) Number of Sheets _____		<input checked="" type="checkbox"/> Other (specify) _____			
<input checked="" type="checkbox"/> Application Data Sheet. See 37 CFR 1.76		Return-Receipt Postcard; Express Mail Certificate			
METHOD OF PAYMENT OF FILING FEES FOR THIS PROVISIONAL APPLICATION FOR PATENT					
<input type="checkbox"/> Applicant claims small entity status. See 37 CFR 1.27.				FILING FEE AMOUNT (\$)	
<input type="checkbox"/> A check or money order is enclosed to cover the filing					
<input checked="" type="checkbox"/> The Director is hereby authorized to charge filing fees or credit any overpayment to Deposit Account Number 08-1935				\$160.00	
<input type="checkbox"/> Payment by credit card. Form PTO-2038 is attached.					
The invention was made by an agency of the United States Government or under a contract with an agency of the United States Government.					
<input checked="" type="checkbox"/> No.					
<input type="checkbox"/> Yes, the name of the U.S. Government agency and the Government contract number are: _____					

Respectfully submitted,

SIGNATURE

Mary Louise Gioeni

TYPED or PRINTED NAME

MARY LOUISE GIOENI

TELEPHONE (518) 452-5600

[Page 1 of 2]

Date JUNE 16, 2004

REGISTRATION NO. 41,779

(if appropriate)

Docket

2309.002P

USE ONLY FOR FILING A PROVISIONAL APPLICATION FOR PATENT

This collection of information is required by 37 CFR 1.51. The information is required to obtain or retain a benefit by the public which is to file (and by the USPTO to process) an application. Confidentiality is governed by 35 U.S.C. 122 and 37 CFR 1.14. This collection is estimated to take 8 hours to complete, including gathering, preparing, and submitting the completed application to the USPTO. Time will vary depending upon the individual case. Any comments on the amount of time you require to complete this form and/or suggestions for reducing this burden, should be sent to the Chief Information Officer, U.S. Patent and Trademark Office, U.S. Department of Commerce, P.O. Box 1450, Alexandria, VA 22313-1450. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Commissioner for Patents, Alexandria, VA

If you need assistance in completing the form, call 1-800-PTO-9199 and select option 2.

CERTIFICATE OF MAILING BY "EXPRESS MAIL"

In Re Application of **ROBERTS et al.**

Title: **MAXIMIZED MICA CONTENT USING A SPECIALTY
THIN HIGH TENSILE BACKING MATERIAL**

Attorney Docket No.: **2309.002P**

"EXPRESS MAIL" MAILING LABEL NO. EV 426313695 US


Date of Deposit: **JUNE 16, 2004**

I hereby certify that this paper is being deposited with the U.S.
Postal Service "Express Mail Post Office to Addressee" service
under 37 CFR 1.10 on the date indicated above and addressed to:

***Commissioner for Patents
P.O. Box 1450
Alexandria, VA 22313-1450***

CHRISTINE C. WEBER

(Typed or printed name of person mailing paper or fee)

A handwritten signature in cursive script, appearing to read "Christine C. Weber", written over a horizontal line.

(Signature of person mailing paper or fee)

DOCUMENTS INCLUDED with this Certificate Express Mail Label No. EV 426313695 US

- * One (1) Acknowledgment Postcard;
- * Provisional Application for Patent Cover Sheet (1 page);
- * U.S. Provisional Patent Application (4 pages); and
- * EFS Application Data Sheet (3 pages)



Provisional Patent Application

Inventor Jonathan Roberts
Co-Inventor: Dana Rackliffe
Co-Inventor: Daniel Bernatchy

1. Title: Maximized mica content using a specialty thin high tensile backing material
2. Background: Natural mica is converted to a continuous sheet product using a process very similar to that used to make paper. This continuous sheet of mica is referred to as mica paper, although it contains no cellulose fibers. Mica exhibits excellent electrical , chemical and high temperature resistance properties that makes it an ideal substrate for applications requiring these attributes. However, the paper manufactured solely from mica has relatively low tensile strength. Most final applications require that the mica paper be reinforced with some other material to prevent the fracturing of the paper while it is being placed into the application. A typical reinforcing backer material is woven glass fabrics. The individual yarns used to produce the glass fabrics are composed of many fine filaments. A common "G" designation contains 204 individual filaments with a nominal diameter of 0.00036 inches. The cross section of these filaments tend to be tubular. A typical total thickness of a glass fabric is 0.002 inches with a tensile strength of 90 pounds.

The basis of the invention is the use of a new glass fabric that is base on flat yarns as opposed to the traditional round yarns. This product is sold by Dielectric Solutions under their trade name GlasFab® Direct. Flat filaments offer significant advantages that can not be achieved with the traditional yarns. These individual advantages offer specific performance characteristic that are in some cases application specific. The following summarizes the advantages and opportunities presented by using the flat filament fabrics

- a. Flat filaments are thinner and weave a thinner fabric than does a fabric using round yarns. This means that for a given final thickness of a typical glass fabric / mica paper composite, one can add more mica paper to the construction. Since it the mica paper that provides the desired characteristics of the insulating composite, one can therefore increase the mica content substantially. For example, a typical construction would be 2 mils

of Glass fabric and 3 mils of mica paper. Using the Dielectric Solution fabric style 1297, the same construction can be redesigned to 1.2 mils fabric and 3.8 mils of mica paper. This is an increase of 27% mica content. Another way to view this is to evaluate the mica to glass ratios. In the first example the mica to glass ratio is 1.5 as compared to 3.2 for the flat yarn example. This has real significance to our end customers, the motor and generator manufacturers. Such an increase of the primary insulation component will allow them to increase the stress on the insulation and to add more copper in the design. For a given machine size, it will allow for more power output. Thinner wall insulation on the coils of a generator will improve the thermal conductivity and allow the unit to operate cooler, which translate to improved operating life.

- b. The flat filaments do not cut each other at the weave cross over and therefore a thinner fabric can maintain the high tensile properties. In the composite form, this means that the improved mica to glass ratio is not done at the sacrifice of tensile strength as would be the case for traditional round yarn based glass fabrics. This is significant in that the mica paper glass composites require a high tensile for final use by the customer.
- c. Flat filaments provide significantly more surface area for bonding the fabric to the mica paper than does the round yarn based fabric. This is significant in that the bond at the interface between the glass fabric and the mica paper is often a point of failure during the customer application. Therefore one tries to maximize this interface bonding. The natural geometry of the flat yarn automatically yields a significantly improved bond over the round yarn based fabrics. This also means that the total resin content used to bond the fabric to the mica paper can be reduced resulting in a cost reduction.
- d. Along the same lines as a., the volume of resin needed to fill the glass yarn is significantly reduced. A reduction in organic volume translates to improved voltage endurance performance of the insulation and better thermal conductivity of the insulation.
- e. For insulating individual wires using the mica paper / glass fabric composite, one can take advantage of the thin glass to produced the desired thinner insulation. Again, for the same allowed space, the thinner insulation will allow for more copper, which translates to more power output.

- f. Round yarn based fabrics in mica composites cause heavy ridges in the wrapped conductors. The flat yarn will yield a smoother and thinner wrap. In the case of insulated round wire, the smooth surface is desirable when extruding over the conductor. The final extruded layer on the wire can be thinner and smoother.

3. Inventors

- a. Jonathan Whitney Roberts
484 Salter Hill rd.
Arlington, VT 05250
802-375-2748
Citizen : USA
 - b. Dana James Rackliffe
503 Post Road
Rutland, VT 05701
(802) 770-5931
Citizen: USA
 - c. Daniel Richard Bernatchy
41 Holiday Farm Road
Bridgewater Corners
VT 05034
802-672-1234
Citizen: USA
4. Mica tape incorporating the specialty thin high tensile backing material is manufactured using the methods of US Patent Nos. 4,286,010, 4,374,892 and/or 4,704,322.
5. Description of flat glass specialty thin high tensile backing material, manufactured according to US Patent No. 6,581,257:

Dielectric Solutions has developed a process that produces an ultra-lightweight glass fiber fabric that is thinner and stronger, with improved electrical and thermal properties, in half the number of fabrication steps of leading competitors' products.

Two key elements distinguish Dielectric's process and end product: the fabric is made with yarns that are twist free, and the final fabric finish is applied before rather than after weaving. Dielectric has accomplished this by producing its own glass fiber, rather than relying on outside suppliers as its competitors do.

"Traditional glass fabric is made from yarns that are twisted like a rope, to give them additional strength," says Kadar. "Dielectric Solutions removes the twisting completely. The result is ribbon-like yarn that yields a very flat fabric where fibers are uniformly distributed."

Flatter fabric is a benefit for applications requiring a thinner, smoother surface. Dielectric's glass fabrics are thin enough to see straight through them.

"The fabric weighs as little as 1 oz. per square yard, containing glass fibers that are only 5 microns in diameter," explains Kadar. "That's about 1/20th the diameter of a normal human hair."

Fibers so small can be quite brittle, which is why traditional glass fabrication processes require that the fibers are coated with a chemical protective coating prior to weaving. This protective coating is then removed and a final finish is applied prior to shipment of the fabric to a customer.

"Typically, this final finish is put on after weaving to ensure compatibility with the customer's process," Kadar points out. At Dielectric Solutions, the final finish the customer wants is applied upfront in the first step, when we form the glass fibers. The change makes for a cleaner, higher-quality product that is also much stronger.

"Dielectric Solutions' process affords greater flexibility and eliminates inefficiencies. It's designed to be more responsive and better adapted for customized products with small volume," says Kadar. "Simply put, it performs better."

APPLICATION DATA SHEET

Electronic Version v14

Stylesheet Version v14.0

Title of Invention	MAXIMIZED MICA CONTENT USING A SPECIALTY THIN HIGH TENSILE BACKING MATERIAL	
Application Type: provisional, utility Attorney Docket Number: 2309.002P		
Correspondence address: Customer Number: 23405 *23405*		
Inventors Information: <u>Inventor 1:</u> Applicant Authority Type: Inventor Citizenship: US Given Name: Jonathan Middle Name: Whitney Family Name: ROBERTS City of Residence: Arlington State of Residence: VT Country of Residence: US Address-1 of Mailing Address: 484 Salter Hill Road Address-2 of Mailing Address: City of Mailing Address: Arlington State of Mailing Address: VT Postal Code of Mailing Address: 05250 Country of Mailing Address: US Phone: Fax: E-mail: <u>Inventor 2:</u> Applicant Authority Type: Inventor		

Citizenship: US
Given Name: Dana
Middle Name: James
Family Name: RACKLIFFE
City of Residence: Rutland
State of Residence: VT
Country of Residence: US
Address-1 of Mailing Address: 503 Post Road
Address-2 of Mailing Address:
City of Mailing Address: Rutland
State of Mailing Address: VT
Postal Code of Mailing Address: 05701
Country of Mailing Address: US
Phone:
Fax:
E-mail:

Inventor 3:

Applicant Authority Type: Inventor
Citizenship: US
Given Name: Daniel
Middle Name: Richard
Family Name: BERNATCHY
City of Residence: Bridgewater Corners
State of Residence: VT
Country of Residence: US
Address-1 of Mailing Address: 41 Holiday Farm Road
Address-2 of Mailing Address:
City of Mailing Address: Bridgewater Corners
State of Mailing Address: VT
Postal Code of Mailing Address: 05034
Country of Mailing Address: US
Phone:
Fax:

E-mail: